

PRODUCT DATA SHEET

Sikagard[®]-740 W

SILANE BASED REACTIVE WATER REPELLENT PENETRATING SEALER

PRODUCT DESCRIPTION

Sikagard[®]-740 W is a one part low viscosity, reactive impregnation for concrete and cementitious substrates based on concentrated Silane emulsion. Sikagard[®]-740 W complies with the requirements of NCHRP Report 244 Series II & IV. Sikagard[®]-740 W is classified under the ALBERTA infrastructure and transportation specifications. Sikagard[®]-740 W complies with the highest requirements of EN 1504-2 for hydrophobic Impregnation (penetration depth class II & resistance to freeze-thaw cycles and chloride ion penetration).

USES

Sikagard[®]-740 W is used as water-repellent penetrating sealer (hydrophobic treatment) for absorbent substrates such as:

- Walkways and ramps
- Industrial floors
- Exposed aggregate
- Pre-cast or pre-placed concrete
- Masonry
- Parking decks
- Stadiums
- Bridge Decks

CHARACTERISTICS / ADVANTAGES

- Good penetration
- Economic and easy to use
- Reduces capillary water absorption, protection against driving rain and splashing on vertical areas
- Reduction of absorption of aggressive or deleterious agents dissolved in water (i.e. chlorides)
- No change in water vapour permeability
- Increases the resistance of concrete to freeze and thaw cycles and de-icing salts
- Water based emulsion, Low VOC
- Resistant to sea water
- Ready to use

PRODUCT INFORMATION

| | |
|---------------------------|--|
| Chemical Base | Alkoxysilane |
| Packaging | 5 gal. (19 L) pail and 55 gal. (208 L) drum |
| Appearance / Color | Milky water like liquid emulsion. |
| Shelf Life | 9 months from date of production if stored in unopened, undamaged and original sealed packaging. |

| | | |
|----------------------------|---|--------------------------------|
| Storage Conditions | Store in dry and cool conditions. Protect from moisture and frost. Condition material between 40°F and 95°F prior to application | |
| Active Content | ~40 % | |
| Product Declaration | Alberta DOT Type 1a | 129 ft ² /gal. |
| | Alberta DOT Type 1b | |
| | Water Repellance | 86.3% |
| | Alkali Resistance | 85.3% |
| | Vapor Transmission | 72.3% |
| | NCHRP 224 Series II | 125 ft²/gal. |
| | Water Weight Gain | 85% |
| | Absorbed Chloride | 96% |
| | NCHRP 224 Series IV | 125 ft²/gal. |
| | Absorbed Chloride | 79.1% |

TECHNICAL INFORMATION

| | | | |
|---|----------------------------|------|-------------|
| Freeze Thaw De-Icing Salt Resistance | 90 Day Salt Ponding | | AASHTO T259 |
| | 0.0 - 0.5" | 93% | |
| | 0.5 - 1.0" | 73% | |
| | 1.0 - 1.5" | 74% | |
| | Scaling Resistance | None | ASTM C672 |
| Penetration Depth | <10 mm | | OHD L-34 |

APPLICATION INFORMATION

| | |
|--------------------------------|--|
| Coverage | Coverage is entirely dependent on the porosity of the substrate. Extremely non-porous substrates may only require 1 coat. To ensure proper penetration depth, a field mock up is recommended: ~ 240–380sq.ft/gal |
| Ambient Air Temperature | 40 °F (5 °C) min. / 95 °F (35 °C) max. |
| Substrate Temperature | 40 °F (5 °C) min. / 95 °F (35 °C) max. |
| Waiting / Recoat Times | Can be overcoated with water and solvent based polymer paint - contact the proposed paint manufacturer for recommendations. Sikagard®-740 W can be used as a water repellent primer under many Sikagard® protective coatings. Penetration of water is thus prevented at possible weak spots or in the event of damage to the top coat and the risk of consequential damages such as paint flaking can be reduced. Waiting time: minimum 5 hours, maximum 1 week. |
| Curing Treatment | Sikagard®-740 W does not require any special curing but must be protected from rain for at least 6 hours at 68 °F (20 °C). |

APPLICATION INSTRUCTIONS

SURFACE PREPARATION

Best results are achieved when Sikagard®-740 W is applied on 28 days old concrete – however, due to its high alkali resistance; it is still possible to apply it as early as 3 days – lower penetration might then be expected. Best results are achieved on a dry, very absorbent substrate. All surfaces to be sealed must be dry, clean, sound before application. Remove all grease, curing compounds,

surface treatments, coatings, oils, etc. Preparation Work: Concrete and masonry surfaces must be prepared using mechanical means (sandblast, shotblast, high pressure water, etc.). Cracks in concrete more than 12 mils must be repaired prior to application of the hydrophobic treatment. If using water to clean, substrate should be visibly dry (i.e. no damp/dark patches) before coating. Surface moisture as measured by Tramex® should read 6% or lower

MIXING

Sikagard®-740 W is supplied ready for use and must not be diluted.

APPLICATION

Sikagard®-740 W is applied using a low-pressure spray, airless spray, brush or roller, in a single pass from bottom up taking care not to let the product run. Apply subsequent pass “wet on wet” until the required consumption is achieved.

On horizontal surface, use flooding technique but avoid excessive ponding on the surface.

LIMITATIONS

- Best results are achieved when Sikagard®-740 W is applied on 28 days old concrete – however, due to its high alkali resistance; it is still possible to apply it at an early age – lower penetration might then be expected.
- Areas such as window frames which still need to be painted must be securely covered to avoid contact with Sikagard®-740 W.
- Areas not to be impregnated such as window panes need to be protected from being accidentally contaminated with Sikagard®-740 W.
- Sikagard®-740 W can damage some coatings and bituminous products.
- In rare cases, Sikagard®-740 W might lead to light darkening of concrete, apply sample areas first.
- Cannot be overcoated with limewash or cement paint.
- Apply Sikagard®-740 W onto a sample area to confirm consumption rates versus penetration depth.
- Refer to the latest Method Statement for detailed information regarding surface preparation, application method, etc.

SCAQMD Rule 1113

(A) Used only for reinforced concrete bridge structures for transportation projects within 5 miles of the coast or above 4,000 feet elevation; or for restoration and/or preservation projects on registered historical buildings that are under the purview of a restoration architect.

(B) Penetrates into concrete and masonry substrates and chemically react to form covalent bonds with naturally occurring minerals in the substrate.

(C) Lines the pores of concrete and masonry substrates with a hydrophobic coating, but do not form a surface film.

(D) Improves water repellency at least 80 percent after application on a concrete or masonry substrate. This performance must be verified on standardized test specimens, in accordance with one or more of the following standards: ASTM C67, or ASTM C97/97M, or ASTM C140.

(E) Provides a breathable waterproof barrier for concrete or masonry surfaces that does not prevent or substantially retard water vapor transmission. This performance must be verified on standardized test specimens, in accordance with ASTM E96/E96M or ASTM D6490.

(F) Meets the performance criteria listed in the National Cooperative Highway Research Report 244 (1981), sur-

face chloride screening applications, for products labeled and formulated for vehicular traffic.

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

LOCAL RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

KEEP CONTAINER TIGHTLY CLOSED •KEEP OUT OF REACH OF CHILDREN •NOT FOR INTERNAL CONSUMPTION •FOR INDUSTRIAL USE ONLY •FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates (“SIKA”), the user must always read and follow the warnings and instructions on the product’s most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA’s Technical Service Department at 800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product’s shelf life. User determines suitability of product for intended use and assumes all risks. User’s and/or buyer’s sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. **NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY**

OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 201-933-8300.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet
Sikagard®-740 W
October 2018, Version 01.01
020303010020000043

Sikagard-740W-en-US-(10-2018)-1-1.pdf

